


PROPERTIES AND LIQUEFACTION RISK ON
BULK CARGOES CARRYING GEBENG,
KUANTAN BAUXITE IN ACCORDANCE TO
IMSBC CODE

NORAISHAH BINTI LAMIN

B.ENG (HONS.) CIVIL ENGINEERING
UNIVERSITI MALAYSIA PAHANG



SUPERVISOR'S DECLARATION

I hereby declare that I have checked this thesis and in our opinion, this thesis is adequate in terms of scope and quality for the award of the degree of Bachelor of Civil Engineering.

Signature :

Name of Supervisor : Assoc. Prof. Dr. Muzamir bin Hasan

Position : Director of CERRM
(Centre for Earth Resources Research & Management)

Date : 04 June 2018



STUDENT'S DECLARATION

I hereby declare that the work in this thesis is my own except for quotations and summaries which have been duly acknowledged. The thesis has not been accepted for any degree and is not concurrently submitted for award of other degree.

Signature :
Name : NORAISHAH BINTI LAMIN
ID Number : AA14238
Date : 04 June 2018

PROPERTIES AND LIQUEFACTION RISK ON BULK CARGOES CARRYING
GEBENG, KUANTAN BAUXITE IN ACCORDANCE TO IMSBC CODE

NORAISHAH BINTI LAMIN

Thesis submitted in fulfilment of the requirements
for the award of the degree of
B.Eng (Hons) in Civil Engineering

Faculty of Civil Engineering and Earth Resources
UNIVERSITI MALAYSIA PAHANG

JUNE 2018

To my beloved family.

ACKNOWLEDGEMENT

I would like to express my earnest gratitude to everyone who has helped me along my research. It wouldn't have been possible for me to complete this research without the help from others.

First of all, I would like to express my deepest appreciation to Assoc. Prof. Dr. Muzamir bin Hasan, my supervisor for Research methodology and Pre-project, for providing supervision and valuable guidance throughout this period of time. I would like to thank Assoc. Prof Dr. Muzamir for guiding me in my research full of patience with his experience and knowledge. My sincere thanks go to my lab mate, Masitah Binti Abdullah who helps a lot in carrying out the laboratory testing throughout this research.

Furthermore, I would also like to acknowledge with much appreciation the crucial role of laboratory assistant, who assisted me during this period of time especially with tasks that I am not familiar with, and provide all the help needed to complete my task. I learned a lot from them especially in sample preparation and experiment conducting in geotechnical laboratory.

I would like to express my appreciation to my course mates who assisted me especially during conducting laboratory experiments. Last but not least, I want to thank my family for their support and encouragement for me throughout this period of time.

ABSTRACT

This research is to identify the differences between the geotechnical properties of raw and processed Gebeng bauxite. Raw bauxite deposits usually contain a higher percentage of clay and siliceous materials. The silica present in the bauxite usually are concentrated in the finer grained fraction of the bauxite deposit. The fine particles in bauxite will cause the bauxite to have higher moisture content and increases the risk of liquefaction to occur during the bauxite's transportation in cargo. The main objective of having beneficiation process before cargo transporting is to minimize the silica content which contributes to the finer fraction in bauxite, as well as to improve the geotechnical properties of bauxite so that it passes the specification of International Maritime Solid Bulk Cargoes Code (IMSBC) for cargo shipping purpose. In this research, a series of laboratory tests will be conducted and the results will reflect the geotechnical properties of Gebeng Bauxite and the correlation of the bauxite's properties can be done. Both the raw and processed Gebeng Bauxite samples will undergo moisture content test, specific gravity test, particle size distribution, Field Emission Scanning Electron Microscope (FESEM) and X-ray fluorescence (XRF) to obtain the desired data.

ABSTRAK

Penyelidikan ini bertujuan untuk mengenal pasti perbezaan antara bauksit Gebeng mentah dan bauksit Gebeng yang telah diproses dari segi sifat-sifat geoteknik. Bauksit mentah biasanya mempunyai peratus tanah liat dan bahan-bahan bersilika yang tinggi. Silika yang berada dalam bauksit biasanya menyumbang kepada zarah halus dalam bauksit. Zarah halus yang berada dalam bauksit akan menyebabkan bauksit mengandungi kandungan kelembapan yang tinggi dan meningkatkan risiko pencairan untuk berlaku ketika dalam pengangkutan kargo. Objektif utama untuk menjalankan proses pembasuhan bauksit sebelum pengangkutan kargo adalah untuk mengurangkan kandungan silika yang menyumbang kepada zarah halus dalam bauksit, dan untuk meningkatkan sifat-sifat geoteknik bauksit supaya ia memenuhi spesifikasi yang ditetapkan dalam Kod IMSBC (International Maritime Solid Bulk Cargoes Code) untuk tujuan pengangkutan kargo. Dalam penyelidikan ini, berbagai ujian makmal akan dijalankan dan keputusan ujian makmal tersebut akan melambangkan sifat-sifat geoteknik untuk bauksit Gebeng dan kolerasi untuk sifat-sifat bauksit boleh didapatkan. Kedua-dua bauksit Gebeng mentah dan bauksit Gebeng yang telah diproses akan menjalani ujian kandungan kelembapan, ujian graviti tentu, taburan saiz zarah, Field Emission Scanning Electron Microscope (FESEM) dan X-ray fluorescence (XRF) untuk mendapatkan data yang diinginkan.

TABLE OF CONTENT

| | |
|----------------------------------------|----------------------------|
| SUPERVISOR’S DECLARATION | |
| STUDENT’S DECLARATION | |
| TITLE PAGE | ii |
| DEDICATION | iii |
| ACKNOWLEDGEMENTS | iv |
| ABSTRACT | v |
| ABSTRAK | vi |
| TABLE OF CONTENTS | vii |
| LIST OF TABLES | x |
| LIST OF FIGURES | xii |
| LIST OF SYMBOLS | xiv |
| LIST OF ABBREVIATIONS | xv |
| CHAPTER 1 INTRODUCTION | |
| 1.1 | Background of Research 1 |
| 1.2 | Problem Statement 3 |
| 1.3 | Objectives 4 |
| 1.4 | Significance of Research 4 |
| 1.5 | Scope of Research 5 |
| CHAPTER 2 LITERATURE REVIEW | |
| 2.1 | Introduction 6 |
| 2.2 | Aluminum 6 |
| 2.3 | Bauxite 7 |
| 2.3.1 | Bauxite Geology 8 |
| 2.3.2 | Bauxite Ore to Aluminum 9 |
| 2.3.3 | Bauxite Production 10 |
| 2.3.4 | Bauxite Process 14 |
| 2.3.5 | Bauxite Residue 16 |

| | | |
|-----|--------------------------------------------------------------|----|
| 2.4 | Geotechnical Properties | 17 |
| | 2.4.1 Grain Size Distribution | 17 |
| | 2.4.2 Specific Gravity | 19 |
| | 2.4.3 Moisture Content | 20 |
| 2.5 | Chemical Properties | 21 |
| | 2.5.1 Scanning Electron Microscope | 21 |
| 2.6 | Physical Properties | 25 |
| 2.7 | Environmental Concerns | 26 |
| | 2.7.1 Metals | 26 |
| | 2.7.2 pH | 26 |
| 2.8 | Bauxite Liquefaction | 27 |
| | 2.8.1 Cargo Liquefaction | 27 |
| | 2.8.2 International Maritime Solid Bulk Cargoes (IMSBC) Code | 29 |
| | 2.8.3 Accidents and Loss due to Cargo Liquefaction | 30 |

CHAPTER 3 METHODOLOGY

| | | |
|-----|--------------------------------------------------------------|----|
| 3.1 | Introduction | 31 |
| 3.2 | Sample Collection | 33 |
| 3.3 | Determination of Properties of Gebeng, Kuantan Bauxite | 34 |
| | 3.3.1 Moisture Content Test | 34 |
| | 3.3.2 Particle Size Distribution | 35 |
| | 3.3.3 Specific Gravity | 37 |
| | 3.3.4 X-Ray Fluorescence (XRF) | 38 |
| | 3.3.5 Field Emission Scanning Electron Microscope (FESEM) | 39 |

CHAPTER 4 DISCUSSION

| | | |
|-----|--------------------------------------------------------------|----|
| 4.1 | Introduction | 40 |
| 4.2 | Particle Size Distribution | 40 |
| | 4.2.1 Comparison Between Raw and Processed of Gebeng Bauxite | 41 |
| 4.3 | Moisture Content | 44 |

| | | |
|-----|-----------------------------------------------------|----|
| 4.4 | Specific Gravity | 46 |
| 4.5 | Field Emission Scanning Electron Microscope (FESEM) | 47 |
| 4.6 | X-Ray Fluorescence (XRF) | 49 |
| 4.7 | Comparison with IMSBC Code | 52 |

CHAPTER 5 CONCLUSION

| | | |
|-----|----------------|----|
| 5.1 | Conclusion | 55 |
| 5.2 | Recommendation | 57 |

REFERENCES 58

APPENDIX

| | | |
|---|-------------------------|----|
| A | SIEVE ANALYSIS TEST | 61 |
| B | MOISTURE CONTENT RESULT | 69 |
| C | SPECIFIC GRAVITY RESULT | 73 |

LIST OF TABLES

| Table No. | Title | Page |
|------------------|------------------------------------------------------------------------------------------------------------------|-------------|
| 2.1 | Mineralogy of Tropical Bauxites | 8 |
| 2.2 | World Bauxite Production and Reserves | 12 |
| 2.3 | World Bauxite Resources by Region (Total World Estimates 55-75 Billion Tons) | 13 |
| 2.4 | Summary of Bayer Process | 16 |
| 2.5 | Specific Gravity of Typical Solid | 19 |
| 2.6 | Properties of Bauxite Mineral | 20 |
| 2.7 | Location of Age of Bauxite for SEM Test | 22 |
| 2.8 | Factors That Affects Soil Liquefaction | 27 |
| 2.9 | Extract of Bauxite Schedule as Listed in Appendix 1 of IMSBC Code | 29 |
| 2.10 | Liquefaction Accidents | 30 |
| 3.1 | Quantity Required for Each Laboratory Test | 33 |
| 3.2 | Tests and Standards for The Research | 34 |
| 4.1 | Comparison of Percentage Fine Particles Between Raw and Processed Gebeng Bauxite from Previous Research | 44 |
| 4.2 | Average Moisture Content of Raw and Processed Gebeng Bauxite | 45 |
| 4.3 | Comparison on The Average Specific Gravity of Raw and Processed Gebeng Bauxite from Previous Research Work | 46 |
| 4.4 | Element of Raw and Processed Gebeng Bauxite | 49 |
| 4.5 | Oxides of Raw and Processed Gebeng Bauxite | 50 |
| 4.6 | Comparison on Oxides of Raw and Processed Gebeng Bauxite from Previous Research Work | 51 |

| | | |
|-----|------------------------------------------------------------------------------|----|
| 4.7 | Comparison Between Gebeng Bauxite with Bauxite from another Region | 52 |
| 4.8 | IMSBC Code | 53 |
| 4.9 | Comparison Table Between Raw and Processed of Gebeng Bauxite with IMSBC Code | 54 |

LIST OF FIGURES

| Figure No. | Title | Page |
|-------------------|-------------------------------------------------------------------------------------------|-------------|
| 1.1 | Bauxite Producing Countries | 2 |
| 2.1 | Bauxite Mining Process | 11 |
| 2.2 | The Bayer Process | 15 |
| 2.3 | World Wide Bauxite Residue Production | 17 |
| 2.4 | Bauxite from Little Rock, Arkansas | 18 |
| 2.5 | Pisolites In Bauxite | 18 |
| 2.6 | Bauxite Without Pisolites from Demerara, Guyana | 19 |
| 2.7 | Pleistocene Karstic Bauxite, Samar-Island, Philippine Islands (3000 Magnification) | 22 |
| 2.8 | Miocene Karstic Bauxite, No 2, South Manchester Plateau, Jamaica (10000 Magnification) | 23 |
| 2.9 | Lateritic Bauxite, Fria Mine, Guinean Republic (3000 Magnification) | 23 |
| 2.10 | Lateritic Bauxite near Bamaco, Mali (1000 Magnification) | 24 |
| 2.11 | Tichvin-Type Bauxite, Sinionskoe Mine Near Tichvin, USSR (3000 Magnification) | 24 |
| 2.12 | Liquefaction Due to Cargo Compaction | 28 |
| 3.1 | Flowchart for Project Methodology | 32 |
| 3.2 | Oven Dry Method | 35 |
| 3.3 | Bauxite Sample Is Put In The Sieve Shaker | 36 |
| 3.4 | Hydrometer Jar | 37 |
| 3.5 | Pycnometer | 38 |
| 3.6 | XRF S8 Tiger | 39 |
| 3.7 | JSM 7800F | 39 |

| | | |
|------|----------------------------------------------------------------------------------------------------------|----|
| 4.1 | Particle Size Distribution for M1L1 Sample | 41 |
| 4.2 | Particle Size Distribution for M1L2 Sample | 42 |
| 4.3 | Particle Size Distribution for M1L3 Sample | 42 |
| 4.4 | Particle Size Distribution for OPST Sample | 43 |
| 4.5 | Tabulated of Percentage Fine Particles Between Raw and Processed Gebeng Bauxite Passing 2.5mm | 43 |
| 4.6 | Moisture Content of Raw and Processed Gebeng Bauxite | 45 |
| 4.7 | Tabulated of Average Specific Gravity of Raw and Processed Gebeng Bauxite from Previous Research Work | 46 |
| 4.8 | Magnification of Gebeng bauxite sample under 1000x magnification | 47 |
| 4.9 | Magnification of Gebeng bauxite sample under 2500x magnification | 47 |
| 4.10 | Magnification of Gebeng bauxite sample under 5000x magnification | 48 |
| 4.11 | Magnification of Gebeng bauxite sample under 10 000x magnification | 48 |
| 4.12 | Magnification of Gebeng bauxite sample under 500 000x magnification | 48 |
| 4.13 | Tabulated of Oxides of Gebeng Bauxite After Undergo Beneficiation Process | 50 |

LIST OF SYMBOLS

| | |
|----|----------------|
| °C | Degree Celsius |
| % | Percentage |
| km | Kilometer |
| g | Gram |
| kg | Kilogram |
| mm | Milimeter |
| μm | Micrometer |

ABBREVIATIONS

| | |
|-------|---------------------------------------------|
| pH | Potential hydrogen |
| IMSBC | International Maritime Solid Bulk Cargoes |
| FESEM | Field Emission Scanning Electron Microscope |
| XRF | X-Ray Fluorescence |
| Al | Aluminium |
| Fe | Iron |
| Na | Sodium |
| O | Oxygen |
| Ti | Titanium |
| Si | Silicon |

CHAPTER 1

INTRODUCTION

1.1 BACKGROUND OF RESEARCH

The third most abundant element that exists in the earth's crust is Aluminium which is after silicon and oxygen. It makes up for about the earth's solid surface's weight by 8% (Schreiner, 2004). Aluminium remained so rare and was not segregated until 1825. It was said to be valued more highly compared to silver. Unlike silver and gold, Aluminium in its pure form is too reactive thus it did not occur in this pure state and that's is the reason that this element remained uncovered for so long. Aluminium can be described as a strong, malleable metal element that has low density and high resistant to corrosion. Besides it highly reflective surface properties, aluminium is a good conductor of heat and electricity. Its corrosion resistance and easy shaping characteristic become a reason to be choose in drink cans and roofing materials industry. Alternatively, Aluminium is found and discovered as bauxite, ore which its colour is reddish-brown. As the end-product of bauxite only being exposed, people tend to recognize aluminium rather than bauxite. Therefore, bauxite mining at the area contribute to anxiety of locals as the mines are located near to residential area.

Bauxite is a mixture of hydrous aluminium oxides, aluminium hydroxides, clay minerals and insoluble materials such as quartz, magnetite, hematite, siderite and goethite. In the industrial perspective point of view, Bauxite is considered as a natural material that which can extract alumina from it in a Bayer plant (Lozej, 1993). The alumina will be extracted from bauxite through the Bayer process, where the ore is mixed with sodium hydroxide and then heat up inside a pressure chamber with temperature of 150 °C to 200 °C until the alumina dissolved and then being filtered out. This process

will create waste by-product which is known as bauxite residue or what we called red mud, a heavy metal laden slurry with high alkalinity which can, contain naturally occurring radionuclides at times (Gore, 2015). Nowadays, the bauxite's mining work had reached a number of 220 million tons per year, with Australia as the leading country that provides almost one-third of total production of Bauxite in the world (Gore, 2015). The world's biggest bauxite producing countries was shown in Figure 1.1




Figure 1.1: Bauxite Producing Countries

Source: Gore (2015)

Bauxite mining has become a contentious issue in Kuantan, Pahang. Since Indonesia stopped producing and exporting bauxite ores to China, Malaysia miners take over the labour and later become the world's top producer beating China itself for nearly half of its ore supply. In 2013, around 100,000 tonnes of bauxite are exported and increased to approximately 205 million tonnes in a year. The exports of bauxites hit a high mark of 20 million tonnes in 2015. The most famous excavation area is Gebeng and Bukit Goh Kuantan, Pahang. Unregulated mining bauxite gives crucial impact to the

serving community. Out of 236 active mine sites, only 36 are legal. This means that, for one legal site excavated, another six are being dug up. Red cuts in the hills are seen behind the east coast town of Kuantan. Based on New Straits Times Online (2015), it was reported that Kuantan, Malaysia is facing severe hazard due to mining of bauxite at that area. A scientist team has sounded warning to public that the damage caused from this poorly and undirected regulated mining activity to our environment may be so intense that the ecosystem might not recover to what it was before. The harmful effect on health of Kuantan's public could be disastrous, and this might carry on for generations. They said, this was in inclusion to the problem of where certain points of water intake being at the downstream of most of the bauxite mines. They underrated the risk that all these hazards might be cause by heavy metals, which includes elements such as mercury, arsenic and aluminium, and also not ignoring other pollutants, which enters the rivers during rain.

1.2 PROBLEM STATEMENT

Exploration of earth resources contribute to national economic growth as it involves international market and demand. Therefore, potential mining location of earth resources is identified such for this study is at Gebeng, Kuantan Pahang. The collected area is at Port Kuantan; approximately 5.7 km from study area. Transportation of bauxite from mine to collective area had resulting a leakage of bauxite fine fraction on the road as well as the surrounding area. It can be said that the area had been polluted by the bauxite residue due to improper method of transport. Hence, the study is done to this area to identify the properties of bauxite due to long term exposure to human and surrounding.

Recently, the loss of Bulk Jupiter – a cargo that carries bauxite from Kuantan, Malaysia to China had risen up the concern of industry and public on bauxite liquefaction. The cargo sunk on a voyage from Kuantan to China which is fully loaded with bauxite and is said to be caused by bauxite liquefaction (Bahamas, 2015). Based on Bahamas Maritime Authority (BMA)'s report on Bulk Jupiter (2015), it highlights on the moisture content of the bauxite transported exceeds the IMSBC specification which is 10%. The testing on cargo loaded on Bulk Jupiter were made and the test revealed that the bauxite

REFERENCES

- Authier-Martin, M., Forte, G., Ostap, S., & See, J. (2001). The mineralogy of bauxite for producing smelter-grade alumina. *Journal of the Minerals, Metals and Materials Society*, 53(12), 36–40. <https://doi.org/10.1007/s11837-001-0011-1>
- Bahamas Maritime Authority. (2015). *Report of the marine safety investigation into the loss of a bulk carrier in the South China Sea on January 2nd 2015*. London: Bahamas Maritime Authority. 28-33.
- Bardossy, G., Csanady, A., & Csordas, A. (1978). Scanning Electron Microscope Study Of Bauxites. *Clays and Clay Minerals*, 26. 245 - 262.
- Bardossy, G. (1982). Karst Bauxites (Bauxite deposits on carbonate rocks) Budapest. *Geochimica et Cosmochimica Acta*.
- Bauxite Mining Process. (June, 26 2016). Retrieved from [http://www.hydro.com/en/about-aluminium/Aluminium-life-cycle/Bauxite-mining/\(2016\)](http://www.hydro.com/en/about-aluminium/Aluminium-life-cycle/Bauxite-mining/(2016)).
- Bell, L. C. (2001). Establishment of native ecosystems after mining—Australian experience across diverse biogeographic zones. *Ecological Engineering*, 17(2), 179–186.
- Bray, E. (2008). Mineral Commodity Summaries 2008. *Bauxite and Alumina*, pp. 32-33.
- Brown, T. J., Bide, T., Hannis, S. D., Idoine, N. E., Hetherington, L. E., Shaw, & Kendall, R. (2010). *World mineral production 2004–08*. British Geological Survey.
- Brown, T. J., Wrighton, C. E., Raycraft, E. R., Shaw, R. A., Deady, E. A., Ripplingale, & Iodine, N. (2015). *World mineral production 2009-13*. British Geological Survey.
- Bromfield, C. S. (1967). *Geology of the Mount Wilson Quadrangle Western San Juan Mountains Colorado*. Washington: United States Government Printing Office.
- Donaldson, D., & Benny, R. (2013). *Essential Readings in Light Metals, Alumina and Bauxite*. Hoboken. New Jersey: John Wiley & Sons, Inc. 43-75.
- Fuller, R. (1986). Aluminate toxicity as a factor controlling plant growth in bauxite residue. *Environmental Toxicology & Chemistry*. 905 - 915.
- GL (2015). Bulk Cargo Liquefaction. Norway: DNV GL Group Headquarters. 20.
- Gore, M. S. (2015). Geotechnical Characterization of Bauxite Residue (Red Mud). *Geotechnical Characterization of Bauxite Residue (Red Mud)*. 287.
- Grafe, M., Power, G., & Klauber, C. (2010); “Bauxite residue issues: III. Alkalinity and associated chemistry”; Hydrometallurgy; Vol. 108 (2011); 60-79.

- Greenwood, N., & Earnshaw, A. (2012). *Chemistry of the Elements* (2nd ed.). Elsevier Science.
- Gu (2008). Chinese alumina industry — development, prospect and challenge in the future.
- Harbeck, G.E., Kohler, M.A., Koberg, G.E. (1958). Water-Loss Investigation: Lake Mead Studies. Washington: United States Government Printing Office.
- Hind, A. R., Bhargava, S. K., & Grocott, S. C. (1999). The surface chemistry of Bayer process solids: a review. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 146(1), 359–374.
- Hudson, I. K. (2012) “Aluminum Oxide”; Ullmann’s Encyclopedia of Industrial Chemistry; Aluminum Company of America; Vol. 2; 607-645.
- Hudson, S. (1982). Sur les particularites du diaspoire des bauxites. *Contribution to the Study of Some Bauxite Minerals*, 17(2), pp. 279-287.
- Hobart, M. (2005). *The principal ore of aluminum. Economic Geology One Hundredth Anniversary*, Volume 1, pp. 681-722.
- Indonesia's export ban leaves Malaysia on top. *The Malay Mail*. Retrived from <http://www.malaymail.com/s/922315/indonesia-export-ban-leaves-malaysia-on-top>.
- Johnston, M. (2010); “Alkalinity Conversion of Bauxite Refinery Residues by Neutralization”; *Journal of Hazardous Materials*; Vol. 182 (2010); 710-715.
- Jonas, D. M. (2010). Liquefaction of unprocessed mineral ores - Iron ore fines and nickel ore. Liquefaction of unprocessed mineral ores. 4.
- Jones, B. E. H., Haynes, R.J., & Phillips, I.R. (2011); “Influence of Organic Waste and Residue Mud Additions on Chemical, Physical, and Microbial Properties of Bauxite Residue Sand”; *Environmental Science Pollution Research*; Vol. 18; 199-211.
- Karim, F. N. (2015, January 2015). Kuantan facing severe danger. News Strait Times Online. Retrieved from <http://www.nst.com.my/node/120276/amp>
- Kirkpatrick, D. B. (1996); “Red Mud Product Development”; *Light Metals 1996*; Proceedings of the Technical Sessions at the 125th TMS Annual Meeting; TMS Light Metals Committee; February, 1996; 75-80.
- Liu, L. (2006); “Properties of Red Mud Tailings Produced Under Varying Process Conditions”; *Journal of Environmental Engineering*; ASCE; Vol. 124; No. 3; 254-264.
- Lozej, G.P., & Neil, N.G. (1993). *Geoscience Canada*, 20. Ontario. 8.
- Martin, M. A., Forte, G., Ostap, S., & See, J. (2001). The mineralogy of bauxite for producing smelter-grade Alumina. *JOM*. 36-40.

- Patterson, S. H., Kurtz, H. F., Olson, J. C., & Neeley, C. L. (1986). *World Bauxite Resources*. Washington: U.S. Government Printing Office.
- Roskill (2008). *The Economics of Bauxite and Alumina*. p. 206.
- Pincus, A. G. (1968); “Wastes from Processing of Aluminum Ores”; *Mineral Waste Utilization*; Vol. 1; 40-49.
- Rai, S. (2011); “Neutralization and Utilization of Red Mud for Its better Waste Management”; *Arch. Environmental Science*; Vol. 6; 13-33.
- Schreiner, B. Z. (2004). *Workbook for General Chemistry*. Department of Chemistry. University of Wisconsin-Madison: Stipes Publishing, Champaign, IL.
- Smith, P. (2009). The processing of high silica bauxites — Review of existing and potential processes. *Hydrometallurgy*, 98(1), pp. 162-186.
- Seed, H. Bolton., & Lee, K. L. (1966). Liquefaction of Saturated Sands During Cyclic Loading. *Journal of the Soil Mechanics and Foundations Division*, pp. 105-134.
- Somogyi, F. (1976); “Dewatering and Drainage of Red Mud Tailings”; PhD Dissertation; Department of Civil Engineering; University of Michigan; Ann Arbor, MI; pp 291.
- Topstad, M., & Karlsen, B. (2015). Impacts of the new Indonesian mining regulations, 1.
- Wagh, A. S. (1987); “Settling Properties of Dilute Bayer Process Muds of Alumina Industry in Jamaica”; *Particulate and Multiphase Processes*; Vol. 3 April (1987); 461-469.